

# Technical Data Sheet



www.silfluosilicone.com

## Fluorosilicone Rubber LR-F5600

### Description:

Chemical Name: Flame-retarded Series Fluorosilicone Rubber

Synonyms: Fluorosilicone gum

Equivalents:

### Typical Technical Properties:

Test Item	Standard		
	Test Method	LR-5660	LR-5670
Appearance	Visual	White	
Specific Gravity (g/cm <sup>3</sup> )	ASTM D792	1.46	1.48
Hardness / shoreA	ASTM D2240	60	70
Tensile Strength (MPa)	ASTM D412	6.8	6.5
Elongation At Break (%)	ASTM D412	310	290
Tear Strength (KN/m)	ASTM D624-B	17	17
*Heat Resistance 200°C X 72h	Hardness change / shore A	5	5
	Tensile strength (MPa)	3.85	3.5
	Elongation at break change %	161	154
IRM903 Volume Change % 150°C X 72h	ASTM D471	5.5	5.2
Fuel C Volume change/% 23°C/72h	ASTM D471	20	20
Flame-retardant Level	GBT10707-2008	FV 0	FV 0
Curing Condition	0.7 DBPH, Press cure: 170°C x 15min, Post cure: 200°C x 4h		

The above values are not intended for use in preparing specifications.

Heat resistance additives need to be added to meet the requirements of heat resistance.

### Applications:

It has excellent oil, solvent, good high and low temperature resistance; good flame retardance which meets the UL94V0 highest flame-retardant level.

Nanjing Silfluo New Material Co., Ltd.

1 / 2

Web: [www.silfluosilicone.com](http://www.silfluosilicone.com) Email: [inquiry@silfluo.com](mailto:inquiry@silfluo.com)

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.

# Technical Data Sheet



[www.silfluosilicone.com](http://www.silfluosilicone.com)

## **Processing Advice:**

It is recommended to use 0.6 ~ 1 phr. 2,5-Dimethyl-2,5-di(tert-butylperoxy)hexane(DBPH).

The customer shall decide the optimum curing temperature and time according to the product dimensions and curing methods.

## **Package &Storage:**

Packed in plastic bags placed into reinforced cardboard boxes. Each box contains 2 bags with 10kg per bag. Keep in cool, dry and ventilated place. Keep away from sunlight and fire sources. This product has cold-flow characteristics, should avoid bag breakage in the process of transportation and usage, shelf life is 12 months from the date of production. It is shipped as non-hazardous substance.

Storage beyond the shelf life does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.