Technical Data Sheet



Fluoro Functional Organosilane LS-M517

Description:

Chemical Name: 1H,1H,2H,2H-Perfluorodecyltrimethoxysilane Synonyms: (Heptadecafluoro-1,1,2,2-tetrahydrodecyl)trimethoxysilane Equivalents: ShinEtsu KBM-7803; TSL8133 Molecular Structure:

Molecular Formula: C₁₃H₁₃F₁₇O₃Si Molecular Weight:568.30 CAS NO.: 83048-65-1 EINECS NO.:

Special Features:

Fluoroalkyl functional silane

Typical Technical Properties:

Appearance: Colorless transparent liquid Purity (by GC, %): 98.0 min Refractive Index (20°C): 1.333±0.005 Boiling Point: 80°C Flash Point: N/A Density (20°C, g/cm³): 1.525±0.005

Applications:

1. It is used as coupling agent to improve fluororesin and substance adhesion strength.

2. Used to prepare waterproof, oil-proof, and anti-fouling treatment agents, which can be used in the protection treatment of cultural relics, masonry, metal, wood, etc.

3. Used as a finishing agent to reduce the water holding capacity of natural fiber (wool, cotton, leather, etc.) products, and improve the surface's hydrophobic and antifouling properties.

4. Used in hydrophobic and antifouling treatment for glass surface.

Package & Storage:

In 1kg fluorinated bottle, 25kg pail, 200kg drum.

Keep in cool, dry and ventilated place. Keep away from sunlight and fire sources. Keep in unopened containers, shelf life is 12 months from the date of production.

Storage beyond the shelf life does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Nanjing Silfluo New Material Co., Ltd.

Web: www.silfluosilicone.com Email: inquiry@silfluo.com

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.