# **Technical Data Sheet**



# **High Temperature Silicone Resin LR-H168**

# Description

The resin is polymerized through a specific process using methyl monomer, phenyl monomer, and specialized silane monomers. It features excellent high-temperature resistance and strong self-drying properties.

## **Typical Technical Properties:**

Items	Index
Appearance	Colorless to light yellow transparent
	liquid, opalescence is permitted
Solid content, %	80 ±1
Viscosity (25°C,cp)	≥ 2000
Drying Time ≤	Surface drying 2h, drying by heating 180°C 2h
Heat resistance (Varnish: float type	No peeling, no cracking, no blistering
aluminum powder=4:1, 500±10°C, 3h)	

#### Application

When combined with various pigments and functional materials, it can be used to formulate heat-resistant coatings suitable for exhaust pipes, electrostatic precipitators, stoves, and more. Additionally, the resin can be blended with organic resins such as alkyd, acrylic, polyester, and epoxy to create temperature-resistant coatings for diverse applications, enhancing overall performance.

## Package &Storage:

#### In 200kg drum.

Keep in cool, dry place. Avoid acid and alkali contact. Avoid direct sunlight. Stored and transported as dangerous goods. The shelf life is half a year(can still be used if the product is qualified after the expiration date).

#### **Use Reference:**

1. The diluent used with this product must be free of water, acids, alkalis, amines, and other reactive compounds, as they may negatively impact adhesion, drying, and other properties of the paint film.

2. This product contains toluene and other flammable and volatile solvents. Proper ventilation should be maintained during use. Take precautions against fire, static electricity, and ignition sources. Operators should follow safety protocols and wear appropriate protective gear.

3. Suitable diluents for this product include ketones, esters, toluene, and xylene.

Nanjing Silfluo New Material Co., Ltd.

Web: www.silfluosilicone.com Email: inquiry@silfluo.com

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.