



Phenylsilicone Resin Intermediate LR-TP10

Description:

LR-TP10 Phenylsilicone resin intermediate has excellent high temperature resistance, weather resistance, anti-corrosion, stain repellency, good compatibility with organic resins.

Typical Technical Properties:

Item	LR-TP10-1	LR-TP10-2
Appearance	Colorless clear liquid	Colorless clear liquid
Viscosity (25°C, mPa.s)	90~180	8~20
Specific Gravity	1.16	1.07
Methoxy Content (%)	15~18	15~18



Applications:

It can be used in high temperature resistant coatings, anti-weathering coil coatings, electrical paints, surface decoration and other fields

Package &Storage:

In 25kg pail, 200kg drum.

Keep in cool, dry and ventilated place. Keep away from sunlight and fire sources. Keep in unopened containers, shelf life is 12 months from the date of production. It is shipped as non-hazardous substance.

Storage beyond the shelf life does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Nanjing Silfluo New Material Co., Ltd.

1 / 1

Web: www.silfluosilicone.com Email: inquiry@silfluo.com

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.