



Silfluo LS-M11

Phenyl Functional Silane


Description

Silfluo LS-M11 is Phenyltrimethoxysilane, a trifunctional phenyl-functional trimethoxysilane. The molecule contains one phenyl group and three hydrolyzable methoxy groups on silicon. The trimethoxysilyl group hydrolyzes and condenses with hydroxylated inorganic surfaces or participates in sol-gel network formation; hydrolysis releases methanol. The phenyl group raises thermal stability, refractive index, and UV resistance of derived siloxane networks relative to alkyl-functional analogs. Used in sol-gel coating formulations, inorganic filler surface modification, epoxy molding compound (EMC) coupling, and phenyl silicone resin synthesis. Performance equivalent to Momentive Silquest A-153, Evonik Dynasylan 9116, and Shin-Etsu KBM-103.

Typical Physical Properties

Silfluo Code:	LS-M11
Chemical Name	Phenyltrimethoxysilane
CAS NO.	2996-92-1
EINECS NO.	221-066-9
Formula	C ₉ H ₁₄ O ₃ Si
Appearance	Colorless Transparent Liquid
Density (ρ _{20°C} , g/cm ³)	1.0620±0.0050
Refractive Index (n _{25.D})	1.4680±0.0050
Purity (by GC, %)	99 min

Molecular Structure



Applications

1. Epoxy molding compound (EMC) and electronic encapsulants
Used as coupling agent in EMC formulations to improve adhesion between epoxy resin and silica fillers at lead-free soldering process temperatures.
2. Optical materials and LED encapsulants
Used as RI-raising intermediate in transparent polymer systems for LED encapsulants, lens coatings, and optical fiber cladding.

Nanjing Silfluo New Material Co., Ltd.

1 / 2

Web: www.silfluosilicone.com Email: inquiry@silfluo.com

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.

Technical Data Sheet



www.silfluosilicone.com

3. Phenyl silicone resin and heat-transfer fluid synthesis

Used as synthetic intermediate in phenyl silicone resin and high-temperature fluid production.

4. Sol-gel and hybrid hard coatings

Used in co-hydrolysis sol-gel formulations for protective and decorative hybrid organic-inorganic coatings.

5. Inorganic filler surface modification

Used to surface-treat wollastonite, ATH, silica, and kaolin for improved dispersion and compatibility in high-temperature polymer composites.

Packing

In 25kg pail, 200kg drum and 1000kg IBC.

Safety and Storage

Store in a cool, dry, well-ventilated place away from direct sunlight, heat, and open flames. Keep containers tightly sealed. Store at or below 25° C.

Shelf life: 24 months from manufacture date in original unopened containers stored at or below 25° C.

Product beyond shelf life may still be usable; verify relevant properties before use.