Technical Data Sheet

www.silfluosilicone.com

Silfluo LR-MQ Liquid

Methyl MQ Silicone Resin

Description:

Silfluo LR-MQ Liquid is a methyl MQ silicone resin supplied as a clear solution in toluene or xylene. Produced by co-hydrolysis of tetraalkoxysilane (Q units) and trimethyl-functional silanes (M units), the resin forms a three-dimensional trimethylsilane-terminated polysilicate network with M/Q ratio of 0.60 – 0.80. Low molecular weight cyclics content is below 0.1%, and hydroxyl content is ⩽0.5%.

The pre-dissolved liquid format allows direct incorporation into formulations without powder dispersion steps, at equivalent resin chemistry to the LR-MQ powder grade.

Typical Technical Properties:

Silfluo Code:	LR-MQ
Appearance	Clear liquid
Viscosity (50% Toluene solution, mm^2/s):	4.0
Hydrochloric Acid Content (50% Toluene solution, mm^2/s):	≤10
Molecular Weight:	5000±1000
Hydroxyl Content(%):	≤0.5
M/Q Value:	0.60~0.80



Solubility:

Hydroxyl Silicone Fluid:	●
Methyl Silicone Oil:	●
Vinyl silicone Oil:	●
White Oil:	○
Castor Oil:	○
Paraffin 52:	○
PE wax:	○
Isopropanol:	●
Ethanol:	●

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.

Water:	○
Toluene:	●
Glycerin:	○
Propylene Glycol:	○
Ethyl Acetate:	●
C9-C13 isoparaffins:	●

○=Insoluble ●=Soluble (⩾20%)

Applications:

1. High-Temperature Industrial Defoamers

The base resin for formulating defoamers and foam stabilizers for high-temperature chemical processes and industrial ink manufacturing.

2. Polyurethane Mold Release Agents

Used in PU processing to prepare high-solids release concentrates or solvent-borne anti-blocking agents for demolding and post-coating of molded components.

3. Silicone Pressure-Sensitive Adhesives (PSAs)

Used as a tackifying network resin in addition-cure PSAs, contributing cohesive strength and peel force control for industrial tapes and protective films.

4. Transparent Reinforcing Fillers

Incorporated into addition-cure LSR and transparent elastomer systems to improve mechanical strength, tear resistance, and dimensional stability without reducing optical clarity.

Package &Storage:

In 25kg pail, 200kg drum.

Keep in cool, dry and ventilated place. Keep away from sunlight and fire sources. Keep in unopened containers, shelf life is 24 months from the date of production. Transported as non-hazardous substance.

Storage beyond the shelf life does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.