Technical Data Sheet

www.silfluosilicone.com

Silfluo LR-TMP10

Solid Silicone Intermediate

Descriptions:

Silfluo LR-TMP10 is a 100% active, solid methyl phenyl silicone resin intermediate containing reactive silanol functional groups. Solvent-free and solid at room temperature (softening point 60-90°C), this intermediate is well-suited for powder coating formulations. It demonstrates compatibility and undergoes condensation grafting with the hydroxyl groups of traditional organic resins, including acrylics, polyesters, and epoxies. Whether incorporated via physical dry-blending or chemical copolymerization, LR-TMP10 upgrades the thermal stability, UV weatherability, and chalking resistance of the final coating system without compromising recoatability.

Performance equivalent to Dow DOWSIL™ RSN-6018.

Typical Technical Properties:

Silfluo Code:	LR-TMP10
Chemical Name: Synonyms:	Solid Silanol-Functional Methyl Phenyl Silicone Intermediate Solid Silicone Resin Intermediate, Solvent-Free Methyl Phenyl Siloxane Resin, Flaked Silicone Resin
Appearance	Colorless to light yellow transparent solid
Volatile matter %	≤ 3 %
Softening point (°C)	60- 90
Solubility in toluene(1:1)	Clear and transparent

Features

1. 100% Active Solid Structure: Solvent-free and solid at room temperature, making it the VOC-compliant modifier for advanced dry powder coating systems.
2. Silanol Reactivity: Features silanol groups that readily crosslink and chemically graft onto the backbone of organic resins (epoxies, polyesters, acrylics) to form organic-inorganic hybrid networks.
3. Thermal Upgrading: Elevates the heat resistance of organic coatings, preventing thermal degradation, substrate cracking, and yellowing at elevated temperatures.
4. Weather & UV Resilience: Imparts long-term weatherability, gloss retention, and chalking resistance for coatings subjected to harsh environmental elements.
5. Exceptional Miscibility: Demonstrates compatibility with a wide of organic base resins and dissolves in aromatic solvents (like toluene) for liquid compounding.
6. Recoatability: Provide powerful heat and weather defense while maintaining minimal impact on intercoat adhesion and the recoatability of the finished multi-layer coating system.

Applications

1. Powder Coatings: The modifying resin for heat-resistant and ultra-weatherable powder coatings, allowing for dry-blending, extrusion, and crosslinking without VOC emissions.

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.

2. Heat Industrial Finishes: For liquid compounding (at a recommended minimum of ⩾15% solid weight) or grafting into industrial paints for industrial ovens, and high-temperature processing equipment.
3. Polysiloxane Coatings: Formulated into weather-resistant polysiloxane marine and protective architectural coatings, meeting the rigorous HG/T 4755-2014 industry standards for exceptional salt spray and corrosion resistance.
4. Coil Coatings: Chemically grafted with polyesters to manufacture highly flexible, weather-resistant silicone-modified polyester (SMP) coil coatings for exterior metal cladding and roofing.

Package &Storage:

Generally be packed in 50kg plastic inner lining paper drums, sealed stored in a cool and dry environment under 25°C. The shelf life is one year(can still be used if the product is qualified after the expiration date).

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.