Technical Data Sheet

www.silfluosilicone.com

Silfluo LS-53C

PFPE Modified Acrylic Compound

Description:

Silfluo LS-53C is a perfluoropolyether (PFPE) modified acrylic compound with 30% active content, combining the ultra-low surface energy and slip characteristics of PFPE fluoropolymer segments with the film-forming versatility and resin compatibility of acrylic chemistry.

The PFPE segments migrate to the coating surface during cure, creating a fluorine-enriched interface layer of exceptionally low surface energy — imparting extreme hydrophobicity, oleophobicity, anti-smudge, and easy-clean performance — while the acrylic backbone ensures permanent covalent incorporation into the coating matrix without plasticizer-type migration or bleed-out over time.

Engineered for high-end optical coatings, anti-fingerprint films, consumer electronics surface protection, and functional engineering plastic hardcoats where long-term surface cleanliness, optical clarity, and durability are simultaneously required.

Typical Technical Properties:

Silfluo Code:	LS-53C
Chemical Name:	Perfluoropolyether modified acrylic compound
Synonyms:	PFPE modified acrylic compound
Appearance:	Translucent liquid
Effective Content:	30
Dosage (%):	0.1~10

Features

1. Ultra-low surface energy — dual hydrophobicity and oleophobicity

PFPE segments oriented at the coating surface deliver contact angles typically >100° for water and >70° for oils and fingerprint sebum, preventing adhesion of water droplets, oily contaminants, and fingerprint residues. This dual repellency profile is characteristic of PFPE chemistry and distinguishes LS-53C from silicone or hydrocarbon-based slip additives that provide hydrophobicity but not oleophobicity.

2. Covalent PFPE-acrylic architecture — permanent performance

The acrylic backbone co-cures or co-polymerizes with the coating resin matrix, permanently anchoring the PFPE segments without plasticizer-type migration to the substrate interface or loss during cleaning and weathering. Long-term anti-smudge and easy-clean performance is maintained through repeated cleaning cycles and UV exposure.

3. Anti-smudge and easy-to-clean surface tactile quality

Low coefficient of friction (COF) surface created by PFPE enrichment provides a smooth, frictionless tactile feel on high-touch surfaces — critical for smartphone screen protectors, optical lenses, and electronic device casings where both anti-fingerprint performance and user haptic experience are specified.

4. Broad resin compatibility — optical clarity preserved

Acrylic backbone provides compatibility with UV-curable acrylate, PMMA, PC, and PET coating systems at recommended dosage levels. Phase separation and haze at optimized loading levels are minimized; verify

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.

optical clarity in the specific formulation and substrate combination.

5. Chemical stability and weatherability

PFPE segment — fully fluorinated polyether backbone — exhibits exceptional resistance to UV degradation, aggressive cleaning agents, solvents, and harsh environmental exposure, maintaining surface performance integrity over the product service life.

Applications

1. Anti-smudge and anti-fingerprint coatings — displays and optical films

Formulated into UV-curable AF transparent coatings for smartphone screen protective films, LCD/OLED display surfaces, optical lenses, and optical discs. PFPE surface enrichment provides fingerprint repellency, easy wipe-clean performance, and maintained optical clarity under repeated contact and cleaning.

2. Consumer electronics and appliance surface protection

Used as anti-graffiti and anti-fouling topcoat additive for external casings of white goods and consumer electronics. Protects surfaces from permanent ink, stains, and accelerated wear under daily-use contact conditions.

3. Engineering plastic hardcoats — PC, PMMA, PET

Incorporated into surface treatment hardcoats for polycarbonate, PMMA, and PET substrates to improve surface slip (COF reduction), chemical resistance, and long-term weathering durability without compromising optical transmission or haze values.

Packing

In 1kg fluorinated bottle, 25kg pail and 200kg drum.

Safety and Storage

Keep in a cool, dry, and well-ventilated environment, strictly avoiding direct sunlight, heat, and ignition sources. The shelf life is 12 months from the date of manufacture when stored in original unopened containers. Classified as a non-hazardous substance for transport and handling. Storage beyond the shelf life does not necessarily mean the product is unusable; however, the properties required for the intended use must be thoroughly checked for quality assurance reasons prior to application.

The offered information of this docs is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are fully satisfactory for end use. Suggestions of use shall not be taken as inducements to infringe any patent. Please confirm with us prior to any problems.